



Boulevard Drain Paver





ASTM #8 Aggregate
jointing material




Heavy
Commercial





	Colour	
	White - Smooth	
Cinder Grey - Smooth		
Charcoal - Smooth		
Light Charcoal - Smooth		
Black ETX - Smooth		
Light Grey - Smooth		
Beige Grey - Smooth		
Beige - Smooth		

	Colour	
	Cinder Grey - Granitech	
Light Charcoal - Granitech		
Charcoal - Granitech		
Light Grey - Granitech		
Beige Grey - Granitech		
Beige - Granitech		
Opal White - Granitech		
Stanstead Grey - Granitech		
Cambrian Brown - Granitech		
Cambrian Black - Granitech		




	209 x 209	
	Dimensions mm	Dimensions in.
	100 x 209 x 209	4 x 8 1/4 x 8 1/4
	Unit/area	22.9 units/m ² / 2.13 units/ft ²
Cube ft ³	56.4 / 9.4 per row	

Mass/ft ²	22.33 kg	49.13 lb
Mass/ft ²	23.63 kg	51.99 lb
Mass/ft ²	28.83 kg	63.40 lb



	150 x 300	
	Dimensions mm	Dimensions in.
	100 x 150 x 300	4 x 5 7/8 x 11 13/16
	Unit/area	22.22 units/m ² / 2.06 units/ft ²
Cube ft ³	69.78 / 11.63 per row	

Mass/ft ²	22.33 kg	49.13 lb
----------------------	----------	----------



TECHNICAL INFORMATION

Product	Standard	Flexural Strength	Compressive Strength	De-icing salts freeze-thaw durability	Density	Absorption	Dimension Tolerance*
Boulevard Drain Paver	CSA A231.2	N/A	μ 50 MPa ≥ 45 MPa	225 g/m ² after 28 cycles 500 g/m ² after 49 cycles	N/A	N/A	Length: -1.0 to +2.0 mm Width: -1.0 to +2.0 mm Height: ±3.0 mm

Boulevard Drain 209 x 209: Joint spacing is 12 mm (0.47 in.) which allows an initial surface infiltration rate of +/-17 387mm/hr. / Boulevard Drain 150 x 300: Joint spacing is 12 mm (0.47 in.)

Cover the snow removal tools with Teflon or neoprene protectors to minimize the risk of damage from scratches or concrete shards. Laying patterns: These laying patterns are by way of example only and represent only a few of many possibilities. Permacon shall not be responsible for the excess or shortage of pavers resulting from installation according to these laying patterns.