Boulevard TLI 90 Crescendo 320 Paver


























	Dimensions mm	Dimensions in.
A	90 x 320 x 240	3 1/2 x 12 5/8 x 9 1/2
В	90 x 320 x 320	3 1/2 x 12 5/8 x 12 5/8
С	90 x 320 x 360	3 1/2 x 12 5/8 x 14 3/16
D	90 x 320 x 400	3 1/2 x 12 5/8 x 15 3/4
E	90 x 320 x 440	3 1/2 x 12 5/8 x 17 5/16
Cube ft²	86.8	12.4 per row

Mass/ft²	19.36 kg	42.6 lb
Mass/ft²	20.65 kg	45.4 lb
Mass/ft²	25.55 kg	56.2 lb


Sold separately




Laying Patterns



Linear



Linear 50% ABCDE + 50% Large Rectangle



Linear Small Rectangle

TECHNICAL INFORMATION

Product	Standard	Flexural Strength	Compressive Strength	De-icing salts freeze-thaw durability	Density	Absorption	Dimension Tolerance*
Boulevard TLI 90 Crescendo 320 Paver 320 x 240 320 x 320 320 x 360 320 x 400 320 x 440	CSA A231.2	N/A	μ 50 MPa ≥ 45 MPa	225 g/m² after 28 cycles 500 g/m² after 49 cycles	N/A	N/A	Length: -1.0 to +2.0 mm Width: -1.0 to +2.0 mm Height: ±3.0 mm

Boulevard TLI 100 Crescendo 300 Paver
















Colour
White - Smooth
Cinder Grey - Smooth
Charcoal - Smooth
Light Charcoal - Smooth
Black ETX - Smooth
Light Grey - Smooth
Beige Grey - Smooth
Beige - Smooth




	Dimensions mm	Dimensions in.
A	100 x 300 x 400	4 x 11 13/16 x 15 3/4
В	100 x 300 x 500	4 x 11 13/16 x 19 11/16
С	100 x 300 x 600	4 x 11 13/16 x 23 5/8
Unit/area	22.8 kg	50.16 lb
Cube ft²	77.52	9.69 per row


Mass/ft² 22.8 kg 50.16 lb
Units are not sold separately



Laying Patterns



Linear 70% ABC + 30% D



Linear 100% D

TECHNICAL INFORMATION

Product	Standard	Flexural Strength	Compressive Strength	De-icing salts freeze-thaw durability	Density	Absorption	Dimension Tolerance*
Boulevard TLI 100 Crescendo 300 Paver 300 x 400 300 x 500 300 x 600	CSA A231.2	N/A	µ 50 MPa ≥ 45 MPa	225 g/m² after 28 cycles 500 g/m² after 49 cycles	N/A	N/A	Length: -1.0 to +2.0 mm Width: -1.0 to +2.0 mm Height: ±3.0 mm



Boulevard TLI 150 Crescendo 125 **Paver**
















	Colour
₹Γ—٦	White - Smooth
	Cinder Grey - Smooth
, – –	Charcoal - Smooth
	Light Charcoal - Smooth
	Black ETX - Smooth
	Light Grey - Smooth
	Beige Grey - Smooth
	Beige - Smooth

		Colour
ed G		Cinder Grey - Granitech
extured	222	Light Charcoal - Granitech
		Charcoal - Granitech
		Light Grey - Granitech
		Beige Grey - Granitech
		Beige - Granitech
		Opal White - Granitech
		Stanstead Grey - Granitech
		Cambrian Brown - Granitech
		Cambrian Black - Granitech

Α		
^	Manual	Α
В		В
	III III III III	С
С		B C D
		E
D	Trans.	F
		Cube ft ²
Ε	The same of the sa	Cube ft ²
		Cube ft ²
F	Illing	


	Dimensions mm	Dimensions in.
A	150 x 125 x 333.33	5 7/8 x 4 15/16 x 13 1/8
В	150 x 125 x 416.67	5 7/8 x 4 15/16 x 16 3/8
С	150 x 125 x 458.33	5 7/8 x 4 15/16 x 18
D	150 x 125 x 500	5 7/8 x 4 15/16 x 19 11/16
E	150 x 125 x 541.67	5 7/8 x 4 15/16 x 21 5/16
F	150 x 125 x 583.33	5 7/8 x 4 15/16 x 23
Cube ft²	53.80	10.76 per row
Cube ft²	53.80	10.76 per row
Cube ft²	43.04	10.76 per row

Mass/ft ²	32.6 kg	71.7 lb	
Mass/ft ²	34.4 kg	75.7 lb	
Mass/ft²	43.6 kg	95.9 lb	
			ī



Typical Row

Laying Pattern



TECHNICAL INFORMATION

Product	Standard	Flexural Strength	Compressive Strength	De-icing salts freeze-thaw durability	Density	Absorption	Dimension Tolerance*
Boulevard TLI 150 Crescendo 125 Paver 125 x 333.33 125 x 416.67 125 x 458.33 125 x 500 125 x 541.67 125 x 583.33	CSA A231.2	N/A	µ 50 MPa ≥ 45 MPa	225 g/m² after 28 cycles 500 g/m² after 49 cycles	N/A	N/A	Length: -1.0 to +2.0 mm Width: -1.0 to +2.0 mm Height: ±3.0 mm



Boulevard TLI 150 Crescendo 320 Paver


















Colour	
White - Smooth	
Cinder Grey - Smooth	
Charcoal - Smooth	
Light Charcoal - Smooth	
Black ETX - Smooth	
Light Grey - Smooth	
Beige Grey - Smooth	
Beige - Smooth	




	Colour
	Cinder Grey - Granitech
222	Light Charcoal - Granitech
_	Charcoal - Granitech
	Light Grey - Granitech
	Beige Grey - Granitech
	Beige - Granitech
	Opal White - Granitech
	Stanstead Grey - Granitech
	Cambrian Brown - Granitech
	Cambrian Black - Granitech




	Dimensions mm	Dimensions in.
A	150 x 320 x 240	5 7/8 x 12 5/8 x 9 1/2
В	150 x 320 x 320	5 7/8 x 12 5/8 x 12 5/8
С	150 x 320 x 360	5 7/8 x 12 5/8 x 14 3/16
D	150 x 320 x 400	5 7/8 x 12 5/8 x 15 3/4
E	150 x 320 x 440	5 7/8 x 12 5/8 x 17 5/16
Cube ft²	49.6	12.4 per row
Cube ft²	49.6	12.4 per row
Cube ft²	37.2	1.4 per row

Mass/ft²	32.6 kg	71.7 lb
Mass/ft²	34.4 kg	75.7 lb
Mass/ft²	43.6 kg	95.9 lb

Units are not sold separately



Laying Pattern



Linear

TECHNICAL INFORMATION

Product	Standard	Flexural Strength	Compressive Strength	De-icing salts freeze-thaw durability	Density	Absorption	Dimension Tolerance*
Boulevard TLI 150 Crescendo 320 Paver 125 x 500 250 x 500 500 x 500 750 x 500 200 x 200	CSA A231.2	N/A	μ 50 MPa ≥ 45 MPa	225 g/m² after 28 cycles 500 g/m² after 49 cycles	N/A	N/A	Length: -1.0 to +2.0 mm Width: -1.0 to +2.0 mm Height: ±3.0 mm



Boulevard TLI 200 Crescendo 300 **Paver**

















	Colour
smooth	White - Smooth
	Cinder Grey - Smooth
	Charcoal - Smooth
	Light Charcoal - Smooth
	Black ETX - Smooth
	Light Grey - Smooth
	Beige Grey - Smooth
	Beige - Smooth






	Dimensions mm	Dimensions in.
A	200 x 300 x 300	7 7/8 x 11 13/16 x 11 13/16
В	200 x 300 x 412.5	7 7/8 x 11 13/16 x 16 1/4
С	200 x 300 x 487.5	7 7/8 x 11 13/16 x 19 3/16
D	200 x 300 x 525	7 7/8 x 11 13/16 x 20 5/8
E	200 x 300 x 562.5	7 7/8 x 11 13/16 x 22 1/8
F	200 x 300 x 637.5	7 7/8 x 11 13/16 x 25 1/8
G	200 x 300 x 675	7 7/8 x 11 13/16 x 26 9/16
Unit/area	16 units/m²	1.49 units/ft ²
Cube ft²	46.52	11.63 per row

Mass/ft ²	43.24 kg	95.12 lb		
Mass/ft²	45.64 kg	100.40 lb		
Mass/ft²	58.14 kg	127.90 lb		
Units are not sold separately				



Laying Pattern



TECHNICAL INFORMATION

Product	Standard	Flexural Strength	Compressive Strength	De-icing salts freeze-thaw durability	Density	Absorption	Dimension Tolerance*
Boulevard TLI 200 Crescendo 300 Paver 300 x 300 300 x 412.5 300 x 487.5 300 x 525 300 x 562.5 300 x 637.5 300 x 675	CSA A231.2	N/A	μ 50 MPa ≥ 45 MPa	225 g/m² after 28 cycles 500 g/m² after 49 cycles	N/A	N/A	Length: -1.0 to +2.0 mm Width: -1.0 to +2.0 mm Height: ±3.0 mm

