

# Grande Smooth Wall [≡]


375 Standard	Metric (mm)	Imperial (in.)
	200 x 375 x 1000	7 7/8 x 14 3/4 x 39 3/8
Weight/unit	161 kg	360 lb
Area/layer	5.00 units/m <sup>2</sup>	0.46 unit/ft <sup>2</sup>
Area/cube	1.80 m <sup>2</sup>	19.56 ft <sup>2</sup>
Length/cube	9.00 lin. m	29.60 lin. ft
Qty/cube	9 units	9 units
Weight/cube	1500 kg	3300 lb

Code	Colour
129000448	Grey
129000982	Range Newport Grey <b>N</b>

Production location	Quebec
Can be double stacked	




750 Standard	Metric (mm)	Imperial (in.)
	200 x 750 x 1000	7 7/8 x 29 1/2 x 39 3/8
Weight/unit	328 kg	726 lb
Area/layer	5.00 units/m <sup>2</sup>	0.46 unit/ft <sup>2</sup>
Area/cube	0.80 m <sup>2</sup>	8.70 ft <sup>2</sup>
Length/cube	4.00 lin. m	13.10 lin. ft
Qty/cube	4 units	4 units
Weight/cube	1350 kg	2970 lb

Code	Colour
129000449	Grey

Production location	Quebec
Can be double stacked	




1125 Standard	Metric (mm)	Imperial (in.)
	200 x 1125 x 1000	7 7/8 x 44 5/16 x 39 3/8
Weight/unit	483 kg	1065 lb
Area/layer	5.00 units/m <sup>2</sup>	0.46 unit/ft <sup>2</sup>
Area/cube	0.60 m <sup>2</sup>	6.45 ft <sup>2</sup>
Length/cube	3.00 lin. m	9.90 lin. ft
Qty/cube	3 units	3 units
Weight/cube	1450 kg	3190 lb

Code	Colour
129000452	Grey

Production location	Quebec
Can be double stacked	



The information contained in these technical documents is supplied for information purposes only. Any application of the information is the sole responsibility of the installer. The installer must ensure that the installation and use of retaining wall projects comply with local regulations and code requirements. A qualified engineer must be consulted for final design for construction purposes. Oldcastle Building Products Canada, Inc. and its affiliates cannot be held responsible for the improper use of information contained in these technical documents.




## Technical Information

Product	Grande Smooth Wall
Standard	ASTM C 1372
Flexural Strength	N/A
Compressive Strength	20.7 MPa
De-icing salts freeze-thaw durability	N/A
Density	2000 kg/m <sup>2</sup>
Absorption	10.4%
Dimension Tolerance*	Length: ±3.2 mm Width: ±3.2 mm Height: ±3.2 mm

# Grande Smooth Wall

Corner Unit	Metric (mm)	Imperial (in.)
	200 x 500 x 1000	7 7/8 x 19 11/16 x 39 3/8
Weight/unit	213 kg	469 lb
Unit/area	3.33 units/m <sup>2</sup>	0.31 unit/ft <sup>2</sup>
Qty/cube	6 units*	6 units*
Weight/cube	1278 kg	2811 lb

\* 6 units equal: 3 right units, 3 left units

Code	Colour
129000451	Grey
129000983	Range Newport Grey 


Production location Quebec  
Can be double stacked

Step 175	Metric (mm)	Imperial (in.)
	175 x 438 x 1000	6 7/8 x 17 1/4 x 39 3/8
Weight/unit	175 kg	386 lb
Unit/area	1.20 lin. m	19.68 lin. ft
Qty/cube	6 units	6 units
Weight/cube	1070 kg	2358 lb




Code	Colour
16202415	Grey

Production location Quebec  
Can be double stacked

Capping 438	Metric (mm)	Imperial (in.)
	200 x 438 x 1000	7 7/8 x 17 1/4 x 39 3/8
Weight/unit	194 kg	427 lb
Unit/area	5.00 units/m <sup>2</sup>	0.46 unit/ft <sup>2</sup>
Qty/cube	6 units	6 units
Weight/cube	1162 kg	2561 lb

Code	Colour
129000450	Grey
121000483	Range Newport Grey 

Production location Quebec  
Can be double stacked



The information contained in these technical documents is supplied for information purposes only. Any application of the information is the sole responsibility of the installer. The installer must ensure that the installation and use of retaining wall projects comply with local regulations and code requirements. A qualified engineer must be consulted for final design for construction purposes. Oldcastle Building Products Canada, Inc. and its affiliates cannot be held responsible for the improper use of information contained in these technical documents.



## Technical Information

Product	Grande Smooth Wall
Standard	ASTM C 1372
Flexural Strength	N/A
Compressive Strength	20.7 MPa
De-icing salts freeze-thaw durability	N/A
Density	2000 kg/m <sup>3</sup>
Absorption	10.4%
Dimension Tolerance*	Length: ±3.2 mm Width: ±3.2 mm Height: ±3.2 mm